




Shandong Zhuoxing Chemical Co., Ltd.
Zibo Zhuoxing Enterprises Co., Ltd.

TDS of EPEG 3000 (C6 polycarboxylate ether monomer)

Description

EPEG 3000 is a kind of main raw material (polycarboxylate ether monomer) for producing Polycarboxylate superplasticizer with excellent slump retention and good adaptability. It is produced with vinyl ethers of Diethylene Glycol and ethylene epoxide as main raw materials.

Chemical formula



Technical Principle

Due to the special molecular structure, the space resistance of the polyether side chain is reduced, the swing of the side chain is more free, and the cohesion and entanglement of the polyether side chain is improving

Characteristics:

1. Polycarboxylate superplasticizer with excellent slump retention and good adaptability is formed by EPEG 3000 copolymerized with



Shandong Zhuoxing Chemical Co., Ltd.
Zibo Zhuoxing Enterprises Co., Ltd.

acrylic acid. The synthesized PCE has good dispersion and slump retention, high adaptability and good viscosity reducing effects. It is especially suitable for projects using the sand and gravel with poor quality and the high content of sediment or with high requirements for concrete.

2. C4 and C5 macromonomers usually react at 30°C-40°C, while EPEG C6 monomers have very low requirements for reaction temperature, which can be completed at room temperature higher than 5°C without heating.

3. EPEG monomer can be reacted by one-pot method, which means that the prepared dripping solution can be added to the reaction system at one time and the reaction can be completed by stirring for 30-40 minutes. The synthetic water-reducing agent also has excellent performance, which can greatly simplify the production process of polycarboxylate superplasticizer.

Enterprise Quality Standard

1. Appearance: White or light yellow flaky solid

2. Moisture: 0.5% max.

3. Hydroxyl Value mg KOH/g: 17-19



Shandong Zhuoxing Chemical Co., Ltd.
Zibo Zhuoxing Enterprises Co., Ltd.

4.pH value (5% aqueous solution): 8-11

5.Double Bond Retention: 95% min.

Packing: Packed in 25 kg plastic woven bags.

Storage and Transportation

It is non-toxic, nonflammable and can be shipped as general chemical, stored at dry, ventilated place, away from sunshine and rain.

Shelf validity: one year

Contact information:

Shelly Cui

Ella Yang

The seller: Zibo Zhuoxing Enterprises Co., Ltd.

Add: Room 1103, 11th Floor, Yunlong Plaza B, No.28 Huaguang Road, Zhangdian District, Zibo City, Shandong Province, China 255000

Manufacturer: Shandong Zhuoxing Chemical Co., Ltd.

Add: Xinhai Industrial Zone, Wudi County, Binzhou City, Shandong Province, China

Tel/Fax:0086 533 2284032



Shandong Zhuoxing Chemical Co., Ltd.
Zibo Zhuoxing Enterprises Co., Ltd.

Mobile/ Wechat:0086 13053363281, 0086 18615126163,

0086 17865273019

Mail:sales@zhuoxingchem.com shellypce@hotmail.com

sales02@zhuoxingchem.com

Web site:www.zhuoxingchem.com

<http://sdzhuoxing.en.alibaba.com>

<https://www.sdzhuoxingpce.com>





Shandong Zhuoxing Chemical Co., Ltd.
Zibo Zhuoxing Enterprises Co., Ltd.

